1880

Weekly Report of Silver Purchases and Deposits Melted at United States Mint.

Date.		Assay No.	Name of Depositor.	Weight before Melting. Oz.	Dec.	Weight after Melting. Oz.	Dec.	Loss. Oz.	Dec.	Loss per ct.	Gain. Oz.	Dec.	Description of Bullion.	Notes of Melter and Refiner. 27/1/80
Jany	12th	15	Wm H. Lee	57	70	57	60		10	17			Button	Of the 23 melts here
		6	John Stuertz	126	55	125	55	1	00	08			Ning	reported
	13th	7	G. C. Thompson	578	50	533	65	44	85	7 76			Grs, Lake Superior	12 are of plate
		8	Do	101	70	94	50	7	20	7 06			Do	and fine bars,
		9	Do	97	20	97	10		10	10			Spoons, Wtch. Cases, &c.	with a moderate
		20	Do	378	10	368	50	9	60	2 54			Do.	loss of 0.73%; —
		1	E. G. Waters	61	25	59	65	1	60	2 62			D'Pl, Ball, &c.	3 are of base bullion
	14th	2	Thos R. Lee	190	85	190	55		35	18			Bars	with a loss of 4.81%,
	15th	3	G. C. Thompson	139	45	137	70	1	75	1 26			Spoons, &c.	a fair ratio; —
		4	Do	99	70	99	30		40	40			Wtch. Cases, Forks, Pl, &c.	2 of lake bullion,
		5	Do	200	95	200	55		40	20			For. Coin	native lumps,
		6	Do	368	35	367	60		75	20			For. Coin	with a reasonable
	16th	7	Hagstoz & Thorpe	73	40	73	30		10	15			Bar.	average loss of
	17th	8	Simons, Bro. & Co.	62	80	62	45		35	56			Spoons, Wtch. Cases, &c.	7.41%; —
				2536	50	2468	00	68	50	2 70				5 are of coin, with about the usual average loss of 0.23%.

Transferred to Bullion fund during the week 55,692, Oz, Pennsylvania Lead Company; 117,525.20 Oz, Omaha; 21,726.65 Oz, Platt; 96,320.05 Oz, Newark; 99,863.40 Oz, St. Louis; 5,745.60 Oz, U. S. A. O. N. Y., and Foreign Coin which weighed 4,750.30 Oz, before melting and 4,747.50 Oz, after.

1 of the N. York Assay Office.
J. A. C. Booth
M. & R.

For week ending Jany 17th, 1880.

Jany	19th	29	L. R. Snowden	58	40	Withdrawn; not Silver.							Plate
		29	G. C. Thompson	34	10	34	00		10	29			Pl. & Bar
	20th	30	John Stuertz	90	10	88	10	2	00	2 22			Nings
		1	Sailer & Stevenson	1015	45	1015	45						Bars, U. S. A. O. N. Y.
		2	A. J. Neegan	124	55	124	25		30	24			U. S. Coin
	21st	3	Emory, Freed & Co.	100	15	100	10		05	05			For. Coin
	23rd	4	G. C. Thompson	897	05	807	20	89	85	10 01			Bars & Gold
		5	W. H. Sheafer & Co.	124	90	124	30		60	48			For. Coin
		6	E. Netterlinus, Jr.	97	90	95	75	2	15	2 19			Buttons
	24th	7	John Stuertz	142	30	141	65		65	46			Ning
				2626	50	2530	80	95	70	5 94			

Transferred to Bullion fund during the week 5135, 50 Oz, Platt Bars; 27,120 Oz, Omaha; 23,970.90 Oz, St. Louis; 90,660.60 Oz, Newark, and 2464.90 Oz, Foreign Coin which weighed after melting 2463.15 Oz.

For week ending Jany 24th 1880.

J. Robley Dunglison
Register

RG104 E-1 Box 120

Report of Silver Purchases
& Deposits made for
weeks ending: —

January 17th 1880

January 24th 1880

RG104 E-1 Box 120

NARA RG104, Entry 1, Box 120

[Abstract:] Report of Silver Purchases & Deposits melted for weeks ending: - January 17th, 1880, January 24th, 1880.

Weekly Report of Silver Purchases and Deposits Melted at United States Mint.

1880

Date.	Assay No.	Name of Depositor	Weight Before Melting Oz. Dec.	Weight After Melting Oz. Dec.	Loss. Oz. Dec.	Loss per ct.	Gain. Oz. Dec.	Description of Bullion.
Jan'y. 12th	15	Wm. H. Lee	57.70	57.60	.10	.17		Button
	6	John Stuertz	126.55	125.55	1.00	.08		Ring
13th	7	G.C. Thompson	578.50	533.65	44.85	7.76		Grs., Lake Superior
	8	Do	101.70	94.50	7.20	7.06		Do
	9	Do	97.20	97.10	.10	.10		Spoons, Watch Cases, &c.
	20	Do	378.10	368.50	9.60	2.54		Do
	1	E.G. Waters	61.25	59.65	1.60	2.62		D'H., Hall, &c.
14th	2	Thos. R. Lee	190.85	190.55	.35	.18		Bars
15th	3	G.C. Thompson	139.45	137.70	1.75	1.26		Spoons, &c.
	4	Do	99.70	99.30	.40	.40		Watch cases, Forks, &c &c
	5	Do	200.95	200.55	.40	.20		For. Coin
	6	Do	368.35	367.60	.75	.20		For. Coin
16th	7	Hagstoz & Thorpe	73.40	73.30	.10	.15		Bar
17th	8	Simons, Bro. & Co.	62.80	62.45	.35	.56		Spoons, Watch Cases
			2536.50	2468.00	68.50	2.70		

NARA RG104, Entry 1, Box 120

Notes of Melter and Refiner:

S 27/1/80

Of the 23 melts here reported

12 are of plate and fine bars, &c., with a moderate loss of 0.73%; 3 are of bass bullion with a loss of 4.81%, a fair ration; 2 of lake bullion, native lumps, with a reasonable average loss of &. 7.41%; 5 are of coin, with about the usual average loss of 0.23%. 1 of the N. York Assay Office.

Jas. C. Booth
M & R

Transferred to Bullion fund during the week 55,692 oz. Pennsylvania Lead Company; 117,525.20 oz. Omaha; 21,726.65 oz., Platt; 96,320.05 oz. Newark; 99,863.40 oz. St. Louis; 5,745.60 oz. U.S.A.O.N.Y., and Foreign Coin which weighed 4,750.30 oz., before melting and 4,747.50 oz. after.

For week ending Jan'y. 17th, 1880.

Date.	Assay No.	Name of Depositor	Weight Before Melting Oz. Dec.	Weight After Melting Oz. Dec.	Loss. Oz. Dec.	Loss per ct.	Gain. Oz. Dec.	Description of Bullion.
Jan'y. 19th	29	L.R. Snowden	58.40	Withdrawn; not silver				Plate
	29	G.C. Thompson	34.10	34.00	.10	.29		H. & Bar
20th	30	John Stuertz	90.10	88.10	2.00	2.22		Rings
	1	Sailer & Stevenson	1015.45	1015.45				Bars, U.S.A.O.N.Y.
	2	A.J. Keegan	124.55	124.25	.30	.24		U.S. Coin
21st	3	Emory, Freed & Co.	100.15	100.10	.05	.05		For. Coin
23rd	4	G.C. Thompson	897.05	807.20	89.85	10.01		Bars & Gold

	5	W.H. Sheafer & Co.	124.90	124.30	.60	.48		For. Coin
	6	E. Ketterlinne, Jr.	97.90	95.75	2.15	2.19		Buttons
24th	7	John Stuertz	142.30	141.65	.65	.46		Ring
			2626.50	2530.80	95.70	5.94		

Transferred to Bullion fund during the week 5135.50 oz. Platt Bars; 27,120 oz. Omaha; 23,970.90 oz. St. Louis; 90,660.60 oz. Newark, and 2464.90 oz. Foreign Coin which weighed after melting 2463.15 oz.

For week ending Jan'y. 24th 1880.

I. Robley Dungliason
Register.